

KUT PLAST 220

Water Reducing & Retarding Admixture

ADM-02-1110



DESCRIPTION

KUT PLAST 220 is based on a Lignosulphonate. Supplied as a brown liquid it is instantly dispersible in water. **KUT PLAST 220** produces more cohesive workable concrete at constant water/cement ratio with slightly improved strength or can give higher strengths at the same workability or can give cement savings up to 15% at the same water/cement ratio, workability and strength.

KUT PLAST 220 will give extended workability.

USES

KUT PLAST 220 can provide up to 15% reduction in free water without loss of workability, resulting in reduced permeability and early strength gain. Can also be used to give cement savings.

KUT PLAST 220 gives extended workability which is useful when concrete is transported in ready mixed trucks and for avoiding cold joints.

ADVANTAGES

Increased workability: Reduces placing time. **Extended workability:** Some set retardation gives longer working times which are useful for truck transport and for avoiding cold joints.

Improved strength: Water reduction gives higher strengths without cement increase or workability loss.

Reduced permeability: Reduction of water reduces porosity giving improved water impermeability.

Surface finish: Better dispersion of cement particles and increased cohesion minimizes segregation and bleeding and gives improved surface finish for flat work and cast surfaces.

Chloride free: Safe In reinforced concrete.

STANDARDS

KUT PLAST 220 compiles with **BS 5075**, as a water reducing and retarding admixture and **ASTM C-494 - Type D**.

TYPICAL PROPERTIES

- **Calcium Chloride content:** NIL
- **Specific gravity:** 1.17 to 1.19 at 20°C.
- **Air entrainment:** Less than 1 % additional air is entrained.
- **Setting time:** 1 to 4 hours retardation at recommended dosage.
- **Cement compatibility:** Compatible with sulphate resisting and other Portland cements.
- **Durability:** Water reduction gives increase in density and water impermeability, which improves durability.
- **Compressive strength:** Reduction in water/cement ratio will result in up to 25% increase in early age compressive strength.

INSTRUCTIONS FOR USE

Dosage: The optimum dosage for **KUT PLAST 220** should be determined by site trials with the particular concrete mix under prevailing ambient condition.

As a guide the dosage is normally:

0.5-1.2 litres/100 kg cement, an optimum dose of upto 1.4 litre/100 kg cement can be used depending on special circumstances (Hot weather concreting).

Use at other dosages: Dosage outside the normal range can be used to meet particular requirement.

Contact **ASPEC** for advice in these cases.

Overdosing: An over dose of double the intended amount of **KUT PLAST 220** will result in retardation.

The ultimate compressive strength of the concrete will not be significantly impaired, but particular care should be



مصنع الخصوصية لكيماويات البناء
SPECIALITIES CONSTRUCTION CHEMICALS FACTORY

Marketed by: Alghanim Specialities Co. W.L.L
Amghara Industrial Area, P.O.Box: 23595 Safat, 13096 Kuwait
Tel: 1802550 – 400 - Fax: +965 24582548 - Email: sales@spec-kw.com



taken to cure the concrete thoroughly.

Curing: As with all structural concrete, normal methods apply.

TECHNICAL SUPPORT

ASPEC provides technical support service on mix design, admixture selection, evaluation of trials, dispensing equipment etc. Please contact the Technical department in these cases.

Cleaning: Spillages of **KUT PLAST 220** can be removed with water.

Packaging: **KUT PLAST 220** is supplied in **210 liters** drums and in bulk.

Storage: **KUT PLAST 220** should be protected from extremes of temperature. Should the material become frozen, it must be completely thawed and thoroughly mixed before use. **KUT PLAST 220** has a curing minimum shelf life of 12 months provided temperature is kept within the range **5° C to 30° C**.

PRECAUTIONS

HEALTH AND SAFETY

KUT PLAST 220 is non-toxic. Any splashes to the skin should be washed immediately with water. Splashes to the eyes should be washed immediately with water and medical advice should be sought.

Fire: **KUT PLAST 220** is non-flammable.

ASPEC endeavours to ensure that any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

Distributor