

KUT PLAST PCE 502

Superior High Performance Concrete Hyperplasticiser Based On Polycarboxylate Technology

ADM-45-0912



DESCRIPTION

KUT PLAST PCE 502 is a high performance hyperplasticiser developed for applications in the ready mixed and precast concrete industries where the highest durability and performance is required.

Super plasticizing action of **KUT PLAST PCE 502** is different than conventional super plasticizers based on sulfonated melamine and naphthalene formaldehyde condensate, which create electrostatic repulsion of particles. **KUT PLAST PCE 502** initially create the same electrostatic repulsion and further stabilizes the mixes due to static repulsion of long lateral chains linked to the polymer backbone.

USES

The excellent dispersion properties of **KUT PLAST PCE 502** make it the ideal admixture for precast and readymixed concrete where low water cement ratios are required. This property allows the production of very high early and high ultimate strength concrete with minimal voids and therefore optimum density. Due to the strength development characteristics the elimination or reduction of steam curing in precast works be considered as an economical option.

ADVANTAGES

During mixing and placement

- High workability without segregation or bleeding
- Self compacting concrete. Generally no vibration required.
- Can be placed and compacted in congested reinforcement
- Reduced labour requirement
- Improved surface finish
- Chloride free

Effect on hardened concrete properties

- Increased early and ultimate compressive strengths
- Increased flexural strength
- Higher E modulus
- Improved adhesion to reinforcing and stressing steel
- Better resistance to carbonation
- Lower permeability
- Better resistance to aggressive atmospheric conditions
- Reduced shrinkage and creep
- Increased durability

STANDARDS

KUT PLAST PCE 502 is free from chlorides and complies with:

- ASTM C494 Type - G
- ASTM C1017 Type II Plasticizing and retarding.

TYPICAL PROPERTIES

Calcium chloride Content: Nil

Specific gravity: 1.110 to 1.130 to 20°C

Air entrainment: Less than 1% additional air is entrained.

Setting time: 1 - 4 hours retardation depending on dosage and climatic conditions.

Chloride content: Nil to BS 5075



مصنع التخصصية لكيماويات البناء
SPECIALITIES CONSTRUCTION CHEMICALS FACTORY

Marketed by: Alghanim Specialities Co. W.L.L.
Amghara Industrial Area, P.O.Box: 23595 Safat, 13096 Kuwait
Tel: 1802550 – 400 - Fax: +965 24582548 - Email: sales@spec-kw.com



COMPATIBILITY

KUT PLAST PCE 502 is compatible with all Portland cements that meet recognized international standards.

KUT PLAST PCE 502 must not be used in conjunction with any other admixture unless prior approval is received from the **ASPEC** Technical Department.

KUT PLAST PCE 502 is suitable for mixes containing:

- Microsilica
- Pulverised fuel ash
- Ground granulated blast furnace slag cement

INSTRUCTIONS FOR USE

KUT PLAST PCE 502 is a ready to use admixture that is added to the concrete at the time of batching.

The maximum effect is achieved when the **KUT PLAST PCE 502** is added after the addition of 50 % to 70 % of the water.

KUT PLAST PCE 502 must not be added to the dry materials.

Thorough mixing is essential and a minimum mixing cycle, after the addition of the **KUT PLAST PCE 502**, of 60 seconds for forced action mixers is recommended.

Dosage: The normal dosage for **KUT PLAST PCE 502** is between 0.2 and 2 litres per 100 kg of (cementitious material).

Dosages outside this range are permissible subject to trial mixes.

Technical Support: **ASPEC** provides technical support service on mix design, admixture selection, evaluation of trials, dispensing equipment etc. Please contact the Technical Department in these cases.

Curing: As with all structural concrete, normal curing methods apply.

Cleaning: Spillages of **KUT PLAST PCE 502** can be removed with water.

PACKAGING

KUT PLAST PCE 502 is available in 210 litre drums and in bulk tanks upon request

STORAGE

KUT PLAST PCE 502 should be protected from extremes of temperature. Should the material become frozen, it must be completely thawed and thoroughly mixed before use.

KUT PLAST PCE 502 has a minimum shelf life of 12 months provided temperature is kept within the range 5°C to 30°C.

PRECAUTIONS

HEALTH & SAFETY

KUT PLAST PCE 502 is non-toxic. Any splashes to the skin should be washed immediately with water. Splashes to the eyes should be washed immediately with water and medical advice should be sought.

Fire: **KUT PLAST PCE 502** is non flammable.

ASPEC endeavours to ensure that any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

Distributor