

KUT EPOXY TILE GROUT

High Performance Epoxy Resin Based Tile Adhesive & Grout

BTA-08-0412



DESCRIPTION

KUT EPOXY TILE GROUT is a solvent free epoxy resin blended with selected fine fillers. It is supplied as a three component system in pre-weighed quantities ready for on-site mixing and use. Two versions of **KUT EPOXY TILE GROUT** are available.

1.Normal: For working at normal temperatures.

2.Extended Pot life: For working in hot weather conditions above 35°C.

USES

KUT EPOXY TILE GROUT is a high performance epoxy grout with exceptional chemical resistance for bedding and grouting tiles in heavy duty environments. It is used for a single operation bedding and grouting of tiles on horizontal & vertical surfaces. It is used wherever excellent mechanical properties, high chemical resistance combined with a high standard of finish is required such as in swimming pools, hospitals, kitchens, slaughter houses, soft drink factories and steam cleaned areas.

ADVANTAGES

- **Quality:** Factory quality controlled pre-weighed quantities reduces site errors.
- **Adhesion:** Good adhesion to steel, concrete and tiles.
- **Waterproof:** Unaffected by water when cured.
- **Application:** Fast application possible and is easily cleaned off with water during initial set.
- **Chemical Resistance:** Highly resistant to a wide range of industrial chemicals.
- **Versatile:** Suitable for grouting joints from 2mm-20mm widths.
- Full cured product is resistant to Bacterial & Fungal growth.

TYPICAL PROPERTIES

Pot life at 25°C	Normal	ExtendedPot life
	1½ hour	5 hours
Density	1.800kg/ltr	1.800 kg / ltr
Open time	2 hours at 20°C	5-6 hours at 20°C
Adjustability time	2 hours at 20°C	4 hours at 20oC
Initial set	6 hours	12 hours
Initial cure	24 hours	48 hours
Full cure	7 days	14 days

MECHANICAL PROPERTIES

	Method	Value
– Compressive strength:	ASTM-C 579	:75 N/mm ²
– Tensile strength:	ASTM-C 307	:16 N/mm ²
– Bond strength :	ANSI A-118.3E.5.5	: 7 N/mm ²
– Abrasion Resistance	---	: Excellent.
– Impact Resistance	---	: Excellent.

CHEMICAL RESISTANCE

Excellent to most aqueous systems including sewage, urine, salt water, diluted acids, battery acids, concentrated Alkalies, mineral oils, vegetable oils and fats. The tiled surfaces grouted with **KUT EPOXY TILE GROUT** may be steam cleaned.

COLOURS: White, light grey, brown, special beige and dark-grey.

INSTRUCTIONS FOR USE

Application and use of **KUT EPOXY TILE GROUT** should be in accordance with relevant British Standard Codes of Practice for tiling works.

- 1. Surface:** Ensure that substrates to be tiled are structurally sound free from grease and oil and do not have excessive laitance. Good surface preparation is necessary to ensure maximum in-service properties and long term performance.
- 2. Mixing:** Mix by adding all the hardener to the base pack stir for 1 minute, then add the filler component and then stirring thoroughly until a smooth, well



مصنع التخصصية لكيماويات البناء
SPECIALITIES CONSTRUCTION CHEMICALS FACTORY

Marketed by: Alghanim Specialities Co. W.L.L
Amghara Industrial Area, P.O.Box: 23595 Safat, 13096 Kuwait
Tel: 1802550 – 400 - Fax: +965 24582548 - Email: sales@spec-kw.com



mixed paste is obtained. Mixing by use of a slow speed drill and mixing paddle is preferred. Do not split packs or alter the components in any way.

- 3. Bedding:** Apply as a bed of approx. 1-3 mm thickness over a working area of a size which can be properly tiled within the pot-life of the material. For floors apply as a "solid bed". On walls the bed may be applied horizontally ribbed by use of a notched trowel.
- 4. Fixing Tiles:** Fix the tiles into the bed by pressing in place, using twisting action. In the case of wall tiles, begin at the bottom and work upwards, and ensure at least 75% of the tile back is in contact with the epoxy. Ensure that the required joint width is left around each tile and is properly spaced out.
- 5. Grouting:** On horizontal, where bedding and grouting is to proceed in one continuous operation, press the tiles into the epoxy bed sufficiently for the epoxy to ooze through the gap between the tiles.

N.B.: Allow a slight increase in the epoxy bed thickness to allow this.

The epoxy grout between the tiles may then be "trimmed" off and the grouted joints finished With spatula.

Were grouting is carried out after the bed has set and tiles are permanently fixed in place, apply the epoxy grout to the joints by plastic spatula and finish off.

- 6. Cleaning:** After bedding or grouting, any surplus material should be removed before its sets by use of damp cloth or squeegee. Good workmanship to ensure removal of surplus material before it sets is essential throughout the works.
- 7. Equipment Care:** Tools and equipment may be cleaned immediately after use with water. If necessary, **KUT SOLVENT EP** may be used.

PACKING AND YIELD

KUT EPOXY TILE GROUT is available in 6.2 kgs pack.

Yield: 3.4 litres / pack.

COVERAGE

- 1. For Tile Fixing :** Varies depending on the surface smoothness. However, for estimation, one may use about 1.5 - 2.0 litres / M².
- 2. Grouting :** Depends on Joint Width depth and tile size. For a tile size of 200 mm x 100mm x 6 mm and joint width of 5 mm, about 0.480 litre of **KUT EPOXY TILE GROUT** would be required per square meter i.e. in this case, one pack of **KUT EPOXY TILE GROUT** would cover about 7M² of tiled surface.

PRECAUTIONS

Cleaning: Spillages should be absorbed with sand or earth etc., and disposed in accordance with local regulations. Clean tools and equipment with water/solvents immediately after use.

Storage: Store in dry conditions up to 20°C. Shelf life is 12 months.

PERFORMANCE STANDARDS

ASTM-C 881 - Type I, Grade 3

Meets the requirements of **ANSI A 118.3.1976 & ANSI A 108.4**

HEALTH AND SAFETY

KUT EPOXY TILE GROUT should not come in contact with skin and eyes or be swallowed. Avoid prolonged inhalation of vapours. Some people are sensitive to epoxy resins, therefore, protective gloves, goggles and barrier creams should be used. Ensure adequate ventilation and if working in enclosed areas, suitable breathing apparatus must be used. Fully cured resins are inert and hence harmless.

If mixed resin comes in contact with skin, it must be removed before it gets dry by washing with soap and plenty of clean water. If swallowed, seek medical attention immediately. Do not induce vomiting.

ASPEC endeavours to ensure that any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

Distributor