

# KUT FAIRING COAT

## One Component Polymer Modified Fairing Or Levelling Coat

REP-08-1110



### DESCRIPTION

**KUT FAIRING COAT** is a concrete-grey or off-white, single component mortar, based on a blend of portland cements, graded silica sands, water reducing agents and compatible water resistant polymers. The product is designed to give good adhesion and cohesion in plastic state and low water requirement resulting in low porosity and long durability.

### USES

**KUT FAIRING COAT** is used for producing a fair-faced concrete appearance after patch repairs to walls, for levelling uneven surfaces, filling honeycombs in precast units and walls and as a levelling compound to prepare for painting or coating. It is suitable for use in marine structures.

### ADVANTAGES

**Easy to use:** Can be brush, sponge or trowel applied. Workability retained for approximately 40 minutes.

**Constant quality:** Factory controlled pre-packed material eliminates site batching variations.

**Adhesion:** Excellent to sound concrete substrates and steel.

**Chloride free:** Excellent strength development without the use of chlorides.

**Weather resistance:** Water and weather resistant.

### TYPICAL PROPERTIES

Density is 1.9 to 2.0 at 17% water.

**Compressive strength:** 30 N/mm<sup>2</sup> at 28 days tested to BS 4550 with 100 mm cubes cured under restraint at 25°C.

### MIXING

The mix proportions are 4 to 4½ litres of water per 25 kg of powder. Small quantities can be mixed by hand but larger quantities should be mixed with a slow speed drill and paddle, the water should be placed in the container first and the powder added with stirring. Stirring should continue for 2-5 minutes to obtain cohesive paste. For application by

trowel slightly less water should be used.

### SUBSTRATE

The surface should be clean and free of dust, loose particles cement laitence and grease.

### APPLICATION

Absorbent surfaces should be pre-wetted with clean water. Application thickness are normally from 3mm to feather edging, Areas of application should be protected against excessive evaporation caused by high temperatures or strong winds.

The minimum application temperature is 5°C.

The pot life is approximately 1 hour at 20°C.

### YIELD COVERAGE

25 kg gives a yield of 14.75 litres at 17% water. One 25 kg bag covers 14.75 square meters at 1 mm thickness.

### PACKAGING

**KUT FAIRING COAT GREY** and

**KUT FAIRING COAT WHITE** are available in 25 kg packs.

### PRECAUTIONS

**Cleaning:** All equipment must be cleaned with water immediately after use. Mixes containing this product must not be emptied into drainage systems.

**Protection:** All works must be protected from rain & frost until fully hardened.

**Storage:** Shelf life is 12 months when stored in dry conditions at moderate temperature and humidity.

**Fire Resistance:** The product is not flammable.

### HEALTH AND SAFETY

The product is non-toxic but mildly alkaline Gloves should be worn during application. Splashes to the skin or eyes should be, removed with clean water. In the event of prolonged irritation, seek medical advice.



مصنع التخصصية لكيماويات البناء  
**SPECIALITIES CONSTRUCTION CHEMICALS FACTORY**

Marketed by: Alghanim Specialities Co. W.L.L  
Amghara Industrial Area, P.O.Box: 23595 Safat, 13096 Kuwait  
Tel: 1802550 – 400 - Fax: +965 24582548 - Email: sales@spec-kw.com





**ASPEC** endeavours to ensure that any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

**Distributor**