

KUT MOULD RELEASE 'SB'

Chemical Mould Release Oil



MIS-01-1110

DESCRIPTION

KUT MOULD RELEASE 'SB' is a specially formulated blend of a refined pale paraffinic mineral oils and chemicals having release properties which are superior to those of a conventional mould oil. **KUT MOULD RELEASE 'SB'** is supplied as a pale, straw, coloured, liquid ready for direct application. The alkali reactive chemicals promote a water repellent interface which protects both steel and timber formwork whilst ensuring an even colour and texture in the cast concrete. It has a built-in rust inhibitor to protect metal forms from rust or corrosion and a preservative to increase the life of wood forms.

USES

KUT MOULD RELEASE 'SB' is used on metal, wood, plastic, and fibre glass forms, also on pans and tubes for roof and column work. On concrete moulds, over laid plywood and fibre glass, **KUT MOULD RELEASE 'SB'** eliminate expensive form cleaning. On scootcretes, hoist buckets, and paving machine mixers, **KUT MOULD RELEASE 'SB'** offers fast clean-up if applied daily. On aluminium and steel, application of **KUT MOULD RELEASE 'SB'** prior to concrete pours will assure easy removal of mortar and/or concrete.

ADVANTAGES

- Ensures good fair-faced concrete, non-staining and economical.
- Can be used on all types of formwork.
- Inhibits corrosion of steel form work.
- Acts as bond breaker and form cleaner,
- Cuts clean-up time.
- Easy to use.

TYPICAL PROPERTIES

- Specific Gravity : 0.82 to 0.86 at 20°C.
- Temperature Limitation : For application temperatures in

excess of 60°C refer to Technical Department.

- Non-staining : Does not stain concrete and can be used safely with white cement.

INSTRUCTIONS FOR USE

Preparation of used moulds

All traces of adherent material either concrete or Oil deposits must be removed prior to use.

Coating: **KUT MOULD RELEASE 'SB'** can be applied by brush, sponge or conventional mould oil sprayer. If a mould oil sprayer is used care should be taken to ensure that the correct nozzle size is chosen. **KUT MOULD RELEASE 'SB'** should be applied in one continuous even film.

Caution : Excessive application is uneconomical and can lead to surface dusting. All non-absorbent surfaces require only a single application. New unsealed timber surfaces should be recoated if a delay period in excess , of 48 hours is envisaged. After use, the formwork should be brushed or wiped clean of any excess dust prior to re-coating with **KUT MOULD RELEASE 'SB'** as previously described. The use of **KUT MOULD RELEASE 'SB'** minimises the amount of cleaning required prior to re-use of the formwork.

PRECAUTIONS

Fire: Due to the high flashpoint the flammability risk of **KUT MOULD RELEASE 'SB'** is low. Ensure adequate ventilation. Do not use near naked flame or smoke during use.

Storage: Shelf life at least 12 months. Protect from frost. Should material be inadvertently exposed to frost, it must be stirred thoroughly before use.

Flashpoint: Above 60°C.

PACKAGING AND COVERAGE

KUT MOULD RELEASE 'SB' is supplied in 200 litre drums.

Coverage: 20 to 60 m² per litre.

Dependent upon porosity and texture of mould surfaces.



مصنع التخصصية لكيمائيات البناء
SPECIALITIES CONSTRUCTION CHEMICALS FACTORY

Marketed by: Alghanim Specialities Co. W.L.L.
Amghara Industrial Area, P.O.Box: 23595 Safat, 13096 Kuwait
Tel: 1802550 – 400 - Fax: +965 24582548 - Email: sales@spec-kw.com





HEALTH AND SAFETY

Gloves should be worn when handling **KUT MOULD RELEASE 'SB'**. Splashes to skin should be removed with soap and water. Do not use solvent. Goggles should be worn as direct contact with eyes will cause irritation and may cause serious damage if left untreated. Any eye contamination should be washed thoroughly with plenty of water and immediate medical treatment sought. Ensure adequate ventilation.

ASPEC endeavours to ensure that any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

Distributor