

KUT FLEXIBOND

High Solids Acrylic Latex Based Bonding Agent

PPC-09-1110



DESCRIPTION

KUT FLEXIBOND is a high concentration acrylic polymer emulsion blended with selected auxiliary modifying agents to improve the general properties of the cementitious mixes and bonding.

USES

KUT FLEXIBOND is used as a bonding primer for **KUT SUPERCOAT NO.1**, **KUT RENCON "S"** and **KUT AQUAPROOF MEMBRANE**. It is used as a mixing liquid with **KUT TILE GROUT** for improved water resistance and when used with sand cement to produce mortars, sands, floorings, it provides extra flexibility and water resistance. It is recommended as a high quality bond coat primer for sand cement renders. **KUT FLEXIBOND** is recommended for use in internal or external application of thin and thick bed mortars. It is also recommended for use in mortars for tiling over gypsum plaster or panels.

ADVANTAGES

- Improves bond strength and waterproofing of cementitious mortars.
- It improves the general qualities such as flexibility and durability of mortars produced at the job sites.
- It enhances the flexibility of mortars to compensate for thermal movements and thermal shocks minimizing the cracking problems in rendering or tile mortars.
- It is specially formulated as an integral flexible admix for cementitious mixes produced at the job site and used as swimming pool tile bonding mortars.

TYPICAL PROPERTIES

- **Bond Strength:** When **KUT FLEXIBOND** is used as a primer for **KUT RENCON "S"** Tensile bond strengths in excess of 3.4 N/mm² at 28 days are typical values. When used a primer **KUT SUPERCOAT NO.1** bond strengths in excess of 2.3 N/mm² are observed.
- **Temperature limitations:** Do not use below 5°C.

APPLICATION

As a bonding agent:

Use KUT FLEXIBOND as such. Do not dilute with water or solvents of any kind. Pour liquid into suitable container ready for application on to previously prepared substrate. Surface preparation is a key step in successful repairs. Mechanically remove all contaminated loose or damaged concrete. Expose full circumference of any corroded reinforcement bars.

All fine dust and debris should be blown off with oil free compressed air. Pre-soak the repair area thoroughly with water prior to application of **KUT FLEXIBOND** as a primer. Remove excess water with a stiff brush. **KUT FLEXIBOND** is applied using a stippling action working well into the substrate. Do not allow puddling as this may cause slippage of the repair mortar. Apply repair mortars whilst the primer coat is still tacky. Surfaces that have dried out should be reprimed again.

As an admixture for cementitious Mortars:

KUT FLEXIBOND modified cementitious mortars are waterproof and have excellent mechanical properties.

This may be suitable for water-soaked areas such as fountains, swimming pools etc. A typical mix design is given below.

Cement	: 1 part
Fine sand	: 2 parts
KUT FLEXIBOND	: 0.20 parts
Water	: to adjust to required application consistency.

Note: These mortars should be preferably tight mixes to ensure a compact Mortar.

As a curing aid:

KUT FLEXIBOND can be used as a curing aid whilst using repair mortars. It is applied by brush when the mortar surface has dried enough to receive it.



مصنع التخصصية لكيمواويات البناء
SPECIALITIES CONSTRUCTION CHEMICALS FACTORY

Marketed by: Alghanim Specialities Co. W.L.L.
Amghara Industrial Area, P.O.Box: 23595 Safat, 13096 Kuwait
Tel: 1802550 – 400 - Fax: +965 24582548 - Email: sales@spec-kw.com



As an additive for Tiling Mortars and Grouts:

KUT FLEXIBOND can be used as additive for cementitious tiling Mortars and grouts to improve thermal shock resistance and waterproofing characteristics. Please refer to respective datasheets, for its usage an application.

As a liquid latex mortar (Thin Set): For fixing all kinds of ceramic tiles and natural stones. The mix design given below is used as a slurry bond coat for thick set application and as adhesive for thin set application. It is recommended for use in interior-exterior application over concrete cement, ceramic tiles and masonry surface and for water resistant applications such as swimming pool etc.

Mix Design

Portland Cement : 2 to 2.5 kg

KUT FLEXIBOND : Upto 1 kg for desired consistency.

PHYSICAL PROPERTIES

- **Wet density** : 1650 kl/M³.
- **Pot Life** : 2 hrs.
- **Tensile Adhesion (As per BS 5980: 1980 Class AA** : 14 days 1500N.
- **Shear Adhesive Strength: BS 5980: 1980 Class AA:** 20.5 kN
- **Shear Bond Strength: ANSI A 118.4 1985 F-6.2.5:** 3.2 Mpa,
- **Compressive Strength: A 118.4 1985 F-8:** 34 Mpa.
- **Linear Co-efficient of Thermal Expansion (ANSI I C 531-81):** 65 x 10⁻⁷F 117 x10⁻⁷C.
- **Service Rating:** Extra Heavy.
- **Smoke Contribution:** Nil.

PACKAGING

KUT FLEXIBOND is available in 5, 20 and 200 kgs containers.

Coverage: As a bonding primer 5-8 m²/kg.

PRECAUTION

Limitations: Do not work at 5°C or less.

Cleaning: All equipment must be cleaned with water immediately after use. Mixes containing this product must not be emptied into drainage systems.

Protection: All work must be protected from rain, frost until fully hardened.

Storage: Shelf life is 12 months when stored in dry conditions at moderate temperature and humidity. Protect product from frost.

Fire resistance: **KUT FLEXIBOND** is not flammable.

PERFORMANCE STANDARDS

The performance standards of **KUT FLEXIBOND** for conformance and testing are:

ASTM - C - 1042 Type-II, ASTM-C 932

ANSI-A -118.4-1976 Latex Portland Cement Mortar.

It also meets and exceeds the water resistance and bond strength requirements of:

ANSI-136.1-1972 - Organic Adhesive.

ANSI-118. 1-1972-Dry set Portland Cement mortar.

HEALTH AND SAFETY

KUT FLEXIBOND is non-toxic but is mildly alkaline. Gloves should be worn during application. Splashes to the skin or eyes should be removed with clean water. In the event of prolonged irritation, seek medical advice.

ASPEC endeavours to ensure that any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

Distributor